

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date
31 March 2005 (31.03.2005)

PCT

(10) International Publication Number
WO 2005/028104 A1

(51) International Patent Classification⁷: **B01J 29/04** [KR/KR]; 504 Hanmaru Apt., Dunsan-dong,, Seo-gu,, Daejeon 302-773 (KR).

(21) International Application Number:
PCT/KR2004/002174 (74) Agent: **PAIK, Nam-Hoon**; 14th Fl., KTB Network Bldg., 826-14 Yeoksam-dong, Gangnam-ku, Seoul 135-769 (KR).

(22) International Filing Date: 30 August 2004 (30.08.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10-2003-0065380
20 September 2003 (20.09.2003) KR

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicant (for all designated States except US): **KOREA RESEARCH INSTITUTE OF CHEMICAL TECHNOLOGY [KR/KR]**; 100 Jang-dong, Yuseong-gu, Daejeon 305-343 (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **JUN, Ki-Won** [KR/KR]; 305-1602 Expo Apt., Jeonmin-dong, Yuseong-gu, Daejeon 305-333 (KR). **ROH, Hyun-Seog** [KR/KR]; 103-404 Dure Apt., Sinseong-dong, Yuseong-gu, Daejeon 305-345 (KR). **KIM, Jae-Woo** [KR/KR]; 279 Geumam-li, Songsan-myeon, Dangjin-gun, Chungcheongnam-do 343-832 (KR). **OH, Jeon, Keun** [KR/KR]; 305-801 Expo Apt., Jeonmin-dong,, Yuseong-gu,, Daejeon 305-761 (KR). **BANG, Jin Hwan**

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CATALYST FOR DIMETHYL ETHER SYNTHESIS AND ITS PREPARATION METHODS

(57) Abstract: This invention relates to a catalyst for synthesis of dimethyl ether and its preparation methods. More specifically, this invention relates to a catalyst with improved formulation for a highly efficient synthesis of dimethyl ether via dehydration of methanol. These catalysts are composed of hydrophobic zeolites, cations selected from alkali metal, alkaline earth metal, or ammonium along with alumina, silica, or silica-alumina. The methods of manufacturing the catalyst of this invention include (a) combining hydrophobic zeolites and precursors of alkali or alkaline earth metal cations with pastes of inorganic binders (at least one selected from the group consisting of bohemites, silica sol, and clay) and calcining the mixture at high temperature; (b) combining particles, which are obtained by calcining the hydrophobic zeolites impregnated with precursors of alkali or alkaline earth metal cations, with pastes of inorganic binders (at least one selected from bohemites, silica sol, and clay) and calcining the mixture at high temperature; (c) combining hydrophobic zeolites with pastes of inorganic binders (at least one selected from the group consisting of bohemites, silica sol, and clay), calcining the mixture at high temperature, impregnating the calcined product with precursors of ammonium cations and calcining the mixture at high temperature. The catalysts of this invention provide significantly high yields of dimethyl ether because they do not result in the production of hydrocarbon side products and their high catalytic activities are maintained for a prolonged period of time.

WO 2005/028104 A1